

0503 NC WW Lacquer (Water White Clear)

Products Group: Nitrocellulose Base Paint

Items: NC WW Lacquer

- Taralac NC Lacquer Clear is extensively used for polishing of wooden furniture, Anticorrosive metal coating & various industrial uses.
- NC clear lacquer is a transparent liquid & highly viscous, non-hazy & pale yellow, thereby maintaining the natural looks of the wood.
- Taralac Clear Lacquer is a high quality, quick-drying lacquer.
- It is recommended for interior wooden furniture & Metal finishes. You can use Taralac Lacquer Clear to get a Glossy, Matt or Satin finish.

Areas of Application	Metal, Interior Wooden Furniture & as a binder for various product, testing of pigments, Wooden Polish, Nail Polish, Glass Panting, Auto Refinishing etc.
Specific Gravity @30° C	0.92 – 0.98
Solids by Weight	32 – 35 %
Dilution Viscosity @27° C By Taralac Thinner 555/ Standard NC Thinner	Mixing ratio = Sample : Thinner (2 : 1) Viscosity = 50 sec – 60 sec Sample : Thinner (1 : 1) Viscosity = 25 sec – 35 sec
Gloss @ 60°	60 – 70 Unit
Method of Application	Spray or cloth rag
Spray Viscosity	18-20 sec. On Ford Cup B4 at 30°C at a pressure of 30-40 p.s.i. (2.2 to 2.8 kg / cm ²)
Recommended Thinner	Thinner 555 / Thinner 111
Covering Capacity	20-24 sq. mt. /litre per coat (85-100 sq. ft) on non pours surface such as glass or Metal depending on application and film thickness & nature of wood in case of wood.
Number of Coats	Can be recoated multiple times.
Drying time at 30°C	Touch dry 5 - 10 minutes Sanding dry 3 to 4 hours Hard dry – overnight
Recoating time	2 to 4 hours at 30°C for Clear Glossy / Matt
Flash Point	20°C
Finishes	Glossy, Matt or Satin (Smooth & Shiny surface)
Packing	200 ml, 500 ml, 1 lt, 4 lt, 20 lt, 200 lt

Note: NC Clear does not contain **LEAD OR CHROMATE** & certificate can be provided on request.

Storage:

Keep material in a cool place below 25 C. Keep the container tightly closed. **The shelf life is 24 months.**