



**TARALAC®**

# TARA PAINTS & CHEMICALS

(An ISO 9001:2015 Certified Company)

A - 423 / 14, Mahagujarat Industrial Estate, Sarkhej - Bavla Road, Lane Behind Satyam Arcade,  
Village : Moraiya, Ahmedabad - 382 210, Gujarat (India)

Tel: (F): +91 8000011774, E-mail: taralac@hotmail.com , taralac@taralac.com Website: www.taralac.com

## 0504 NC Hi-Glossy Lacquer

**Products Group: Nitrocellulose Base Paint**

**Items: NC Hi-Glossy Lacquer**

- Taralac NC Lacquer Clear is extensively used for polishing of wooden furniture, Anticorrosive metal coating & various industrial uses.
- NC clear lacquer is a transparent liquid & highly viscous, non-hazy & pale yellow, thereby maintaining the natural looks of the wood.
- Taralac Clear Lacquer is a high quality, quick-drying lacquer.
- It is recommended for interior wooden furniture & Metal finishes. You can use Taralac Lacquer Clear to get a Glossy, Matt or Satin finish.

|                                                                                  |                                                                                                                                                                         |
|----------------------------------------------------------------------------------|-------------------------------------------------------------------------------------------------------------------------------------------------------------------------|
| <b>Areas of Application</b>                                                      | Metal, Interior Wooden Furniture & as a binder for various product, testing of pigments, Wooden Polish, Nail Polish, Glass Panting, Auto Refinishing etc.               |
| <b>Specific Gravity @30° C</b>                                                   | 0.92 – 0.98                                                                                                                                                             |
| <b>Solids by Weight</b>                                                          | 32 – 35 %                                                                                                                                                               |
| <b>Dilution Viscosity @27° C<br/>By Taralac Thinner 555/ Standard NC Thinner</b> | Mixing ratio = Sample : Thinner ( 2 : 1 ) Viscosity = 50 sec – 60 sec<br>Sample : Thinner ( 1 : 1 ) Viscosity = 25 sec – 35 sec                                         |
| <b>Gloss @ 60°</b>                                                               | 60 – 70 Unit                                                                                                                                                            |
| <b>Method of Application</b>                                                     | Spray or cloth rag                                                                                                                                                      |
| <b>Spray Viscosity</b>                                                           | 18-20 sec. On Ford Cup B4 at 30°C at a pressure of 30-40 p.s.i. (2.2 to 2.8 kg / cm <sup>2</sup> )                                                                      |
| <b>Recommended Thinner</b>                                                       | Thinner 555 / Thinner 111                                                                                                                                               |
| <b>Covering Capacity</b>                                                         | 20-24 sq. mt. /litre per coat (85-100 sq. ft) on non pours surface such as glass or Metal depending on application and film thickness & nature of wood in case of wood. |
| <b>Number of Coats</b>                                                           | Can be recoated multiple times.                                                                                                                                         |
| <b>Drying time at 30°C</b>                                                       | Touch dry 5 - 10 minutes<br>Sanding dry 3 to 4 hours<br>Hard dry – overnight                                                                                            |
| <b>Recoating time</b>                                                            | 2 to 4 hours at 30°C for Clear Glossy / Matt                                                                                                                            |
| <b>Flash Point</b>                                                               | 20°C                                                                                                                                                                    |
| <b>Finishes</b>                                                                  | Glossy, Matt or Satin (Smooth & Shiny surface)                                                                                                                          |
| <b>Packing</b>                                                                   | 200 ml, 500 ml, 1 lt, 4 lt, 20 lt, 200 lt                                                                                                                               |

**Note:** NC Clear does not contain **LEAD OR CHROMATE** & certificate can be provided on request.

### **Storage:**

Keep material in a cool place below 25 C. Keep the container tightly closed. **The shelf life is 24 months.**

All the information given here are as per the results obtained in laboratory & are given in good faith to guide the user but without any warranty, the actual application results might vary depending on the conditions. We are not responsible for any loss, injury or damage resulting from the use of this information

PDS Ver.No: 0504.01/12112021