



TARALAC®

TARA PAINTS & CHEMICALS

(An ISO 9001:2015 Certified Company)

A - 423 / 14, Mahagujarat Industrial Estate, Sarkhej - Bavla Road, Lane Behind Satyam Arcade,
Village : Moraiya, Ahmedabad - 382 210, Gujarat (India)

Tel: (F): +91 8000011774, E-mail: taralac@hotmail.com , taralac@taralac.com Website: www.taralac.com

0510 NC Sanding Sealer

| | |
|--|--|
| <ul style="list-style-type: none">Taralac NC Sanding Sealer is extensively used for wooden furniture, Anticorrosive metal coating & various industrial uses.It has a good leveling as well as filling property & it offers good adhesion to wood & other substrate.Taralac NC Sealer is a high quality, quick drying lacquer.It is recommended for interior wooden furniture & Metal finishes. You can use Taralac NC Sanding Sealer to get a Glossy, Matt or Satin finish. | |
| Areas of Application | Metal, Interior Wooden Furniture & as a binder for various product, testing of pigments, Wooden Polish, Nail Polish, Glass Panting, Auto Refinishing etc. |
| Specific Gravity @30° C | 0.92 – 0.98 |
| Solids by Weight | 35 – 38 % |
| Dilution Viscosity @27° C By Taralac Thinner 555/Standard NC Thinner | Mixing ratio = Sample : Thinner (2 : 1) Viscosity = 120 sec – 140 sec Sample : Thinner (1 : 2) Viscosity = 18 sec – 30 sec |
| Gloss @ 60° | 0 – 20 Unit |
| Method of Application | Spray or cloth rag |
| Spray Viscosity | 18-20 sec. On Ford Cup B4 at 30°C at a pressure of 30-40 p.s.i. (2.2 to 2.8 kg / cm ²) |
| Recommended Thinner | Thinner 555 / Thinner 111 |
| Covering Capacity | 20-24 sq. mt. / liter per coat (85-100 sq. ft) on non pours surface such as glass or Metal depending on application and film thickness & nature of wood in case of wood. |
| Number of Coats | Can be recoated multiple times. |
| Drying time at 30°C | Touch dry 5 - 10 minutes Sanding dry 3 to 4 hours Hard dry – overnight |
| Recoating time | 0.5 to 2 hours at 30°C for sanding sealer |
| Flash Point | 20°C |
| Finishes | Matt or Satin (Smooth & Shiny surface) |
| Packing | 200 ml, 500 ml, 1 lt, 4 lt, 20 lt, 200 lt |

Note: NC Sanding sealer does not contain **LEAD OR CHROMATE** & certificate can be provided on request.

Storage:

Keep material in a cool place below 250C. Keep the container tightly closed. It has **Shelf life of 12 months.**

All the information given here are as per the results obtained in laboratory & are given in good faith to guide the user but without any warranty, the actual application results might vary depending on the conditions. We are not responsible for any loss, injury or damage resulting from the use of this information

PDS Ver.No.: 0510.01/12112021



TARALAC®

TARA PAINTS & CHEMICALS

(An ISO 9001:2015 Certified Company)

A - 423 / 14, Mahagujarat Industrial Estate, Sarkhej - Bavla Road, Lane Behind Satyam Arcade,
Village : Moraiya, Ahmedabad - 382 210, Gujarat (India)

Tel: (F): +91 8000011774, E-mail: taralac@hotmail.com , taralac@taralac.com Website: www.taralac.com



TARALAC®

All the information given here are as per the results obtained in laboratory & are given in good faith to guide the user but without any warranty, the actual application results might vary depending on the conditions. We are not responsible for any loss, injury or damage resulting from the use of this information

PDS Ver.No.: 0510.01/12112021