

0527 RTU Sealer (60s)

Item: RTU Sealer

- Taralac RTU SEALER is extensively used as a SEALER for various substrates & to be overdone by Hydrographic - It has a good leveling as well as filling property & it offers good adhesion & fast dry properties. - RTU SEALER clear liquid & ready to use, transparent, non hazy & pale yellow, thereby maintaining the natural looks of the substrate	
Areas of Application	As a SEALER for hydrographic
Method of Application	Spray, Brush or cloth rag
Spray Viscosity	18-20 sec. On Ford Cup B4 at 30°C at a pressure of 30-40 p.s.i. (2.2 to 2.8 kg / cm ²)
Recommended Thinner	Solvent Mix 555 or Solvent Mix 111
Covering Capacity	20-24 sq. mt. / liter per coat (85-100 sq. ft) on non pours surface such as glass or Metal depending on application and film thickness & nature of wood in case of wood.
Number of Coats	Can be recoated multiple times.
Drying time at 30°C	Touch dry 5 - 10 minutes Sanding dry 3 to 4 hours Hard dry – overnight
Flash Point	17 °C
Finishes	Smooth & Shiny surface
Packing	1 lt, 4 lt, 20 lt, 200 lt

Note: NC Sanding sealer, NC Clear does not contain **LEAD OR CHROMATE** & certificate can be provided on request.