



TARALAC®

TARA PAINTS & CHEMICALS

(An ISO 9001:2015 Certified Company)

A - 423 / 14, Mahagujarat Industrial Estate, Sarkhej - Bavla Road, Lane Behind Satyam Arcade,
Village : Moraiya, Ahmedabad - 382 210, Gujarat (India)

Tel: (F): +91 8000011774, E-mail: taralac@hotmail.com , taralac@taralac.com Website: www.taralac.com

0553 Silkwood Matt Clear & Shades

Products Group: Single Pack Polyurethane

Items: Silkwood Matt Clear & Shades

SILKWOOD VARNISH is a clear gloss varnish based on modified alkyd resin developed for interior & Exterior wooden surfaces. It has a good colour retention, weather resistance, easy to apply and durable finish.	
Areas of Application	Ideal for all types of woods, hardwoods, joinery, clipboards. It can also be used on untreated wood and previously treated woods. For exterior.
Colour	Clear and Tinted
Viscosity	65 - 75 sec. On Ford Cup B4 at 30° C
% NVM	45 ± 2
Method of Application	By brush or Spray
Spray Application Viscosity	18-20 sec. On Ford Cup B4 at 30°C at a pressure of 30-40 p.s.i. (2.2 to 2.8 kg / cm ²)
Recommended Thinner	Thinner # 555, 111, ST2
Covering Capacity	14 - 16 sq. mt. / liter per coat on non porous surface such as glass or Metal depending on application and film thickness & nature of wood in case of wood.
Number of Coats	Can be recoated multiple times.
Finishes	Glossy & Matt Finish
Packing	200 ml, 500 ml, 1 lt, 4 lt, 20 lt

Surface Preparation:

- Surface must be clean, dry, and free from dirt, oil, grease and other foreign matters. If detergent is used for cleaning, rinse with fresh water.
- The temperature of the substrate should be min 50 C, above the dew point.

All the information given here are as per the results obtained in laboratory & are given in good faith to guide the user but without any warranty, the actual application results might vary depending on the conditions. We are not responsible for any loss, injury or damage resulting from the use of this information

PDS Ver.No.: 0553.01/12112021



TARALAC®

TARA PAINTS & CHEMICALS

(An ISO 9001:2015 Certified Company)

A - 423 / 14, Mahagujarat Industrial Estate, Sarkhej - Bavla Road, Lane Behind Satyam Arcade,
Village : Moraiya, Ahmedabad - 382 210, Gujarat (India)

Tel: (F): +91 8000011774, E-mail: taralac@hotmail.com , taralac@taralac.com Website: www.taralac.com



TARALAC®

All the information given here are as per the results obtained in laboratory & are given in good faith to guide the user but without any warranty, the actual application results might vary depending on the conditions. We are not responsible for any loss, injury or damage resulting from the use of this information

PDS Ver.No.: 0553.01/12112021