



TARALAC®

TARA PAINTS & CHEMICALS

(An ISO 9001:2015 Certified Company)

A - 423 / 14, Mahagujarat Industrial Estate, Sarkhej - Bavla Road, Lane Behind Satyam Arcade,
Village : Moraiya, Ahmedabad - 382 210, Gujarat (India)

Tel: (F): +91 8000011774, E-mail: taralac@hotmail.com , taralac@taralac.com Website: www.taralac.com

1206 NC Shades 3

- TYPE:** Based on nitrocellulose resins and high-quality pigments.
- RECOMMENDED USE:** It is a high-quality Cellulose Nitrate based finish coat ideal for use on Automobiles, Two-wheelers, bus bodies and various industrial products. It gives high gloss, good hardness, colour retention and exterior durability.

PROPERTIES

1. **COLOUR** : As Per TARALAC shade card.
2. **SPECIFIC GRAVITY** : 1.00 to 1.10
3. **VISCOSITY** : 60 ± 5 seconds by flow cup No.4 at 30°C.
(2:1 :: Lacquer : Thinner)
4. **FINISH** : Smooth, free from sagging & wrinkling.
5. **GLOSS** : Glossy, achieves high gloss after rubbing and polishing.
6. **DRYING TIME** : Touch Dry : 10 Minutes
Hard Dry : 30 Minutes
Recoating after : 30 Minutes
Rubbing after : Overnight
7. **SCRATCH HARDNESS** : 1500gms. When fully cured.
8. **FLEXIBILITY & ADHESION** : Good
9. **FLASH POINT** : Highly Inflammable.
10. **Salt Spray Test (IS 101)** : 96 hrs. Passes

- APPLICATION** : By Spray only.
- THINNER** : TARALAC Thinner 555 / 211 / 111.

THEORETICAL SPREADING RATE: 10 – 15 Sq.M./Ltr per coat at 20-25 Microns D.F.T.
(Depending on Shade)

SHELF LIFE: 6 Months in sealed container at normal ambient Temperatures.

REMARKS: Stir well before use.
Surface Preparation has to be done properly.

PACKING : 20 Ltrs., 1 Ltrs., 500 ml., 200 ml.



TARALAC®

TARA PAINTS & CHEMICALS

(An ISO 9001:2015 Certified Company)

A - 423 / 14, Mahagujarat Industrial Estate, Sarkhej - Bavla Road, Lane Behind Satyam Arcade,
Village : Moraiya, Ahmedabad - 382 210, Gujarat (India)

Tel: (F): +91 8000011774, E-mail: taralac@hotmail.com , taralac@taralac.com Website: www.taralac.com

NOTE: Usually NC Finishes are lead & chromate-free, except a few shades, details of which as mentioned below

Lead Free Shades:	White, Crystal White, Bianco, Casablanca White, Crystal White, Diamond White, Francoise White, Marble White, Milky White, New Superior White, Off White, Royal Ivory, Sea White, Super White, Tata Cream, Bayer Cream, Irish Cream, Bayer Blue, Blue Moon, Racing Blue, Vip Blue, Ford Blue, Neptune Blue, Phiroza, Oxford Blue, Matt Black, Sky Blue, Tata Blue, Polynesian Beige, Sandstone, Sandal Paste, Sunny Beige, Ad Grey, Commander Grey, Da Grey, Dustexa, Light Grey, Mahindra Grey, Silver Grey, Smoke Grey, Tata Smoke Grey, Tata Steel Grey, Ape Yellow, Cab Yellow, Gulf Red, Light Gold, Mid Buff, Teak, Light Pink, Imperial Maroon, Fast Blue, Fast Red, Cherry Red, Yellow Oxide, Fast Green, Jet Black, Maroon, New Copper Dust, Violet Mica, Bambi Beige, Golden Beige, Honda Red, Carnation Red, Pewter Grey
Lead Content:	Dawn Glow, Deep Orange, Tata Orange, German Red, Mahindra Red, Mercedes Red, Messey Red, Phoenix Red, Po Red, Signal Red, Tata Ruby Red, Telco Red, Golden Yellow, Lemon Yellow,

TARALAC®

All the information given here are as per the results obtained in laboratory & are given in good faith to guide the user but without any warranty, the actual application results might vary depending on the conditions. We are not responsible for any loss, injury or damage resulting from the use of this information

PDS Ver.No.: 1206.01/30112021