



TARALAC®

TARA PAINTS & CHEMICALS

(An ISO 9001:2015 Certified Company)

A - 423 / 14, Mahagujarat Industrial Estate, Sarkhej - Bavla Road, Lane Behind Satyam Arcade,
Village : Moraiya, Ahmedabad - 382 210, Gujarat (India)

Tel: (F): +91 8000011774, E-mail: taralac@hotmail.com , taralac@taralac.com Website: www.taralac.com

1410 Syn Chasis Grey / Tata Steel Grey

Syn Enamel Paint is a Single Pack First Quality Hi-Gloss Alkyd Enamel Paint, used multi-purposely on various substrates.

ADVANTAGES:

- For interior and exterior surfaces like masonry, steel, wood, asbestos etc.
- Weather resistance and exterior protection.
- Good colour retention.
- Ease of application.
- Excellent for wood and metal surfaces.
- Good hiding power and adhesion.
- Super glossy finish.

TECHNICAL DATA

Areas of application	Wood, Asbestos, masonry, Metal etc.
Thinner recommended	Taralac St Thinner ST – 2
Method of application	Brushing or Spraying
Drying time	Surface dry – 1 – 2 hr Hard dry - less than 18 hours
Viscosity	70 – 80 sec
Volume Solids	Approx 48 – 58%
Specific Graviry	0.90 – 1.15 kg/lt
Finish	Smooth and Glossy
Covering capacity (spreading by brushing on smooth non-absorbent surface)	18 - 24 sq. Mts./ltr/coat depending upon the nature of the substrate at 20 - 25 microns film thickness
Flash Point	Above 30 ⁰ C (86 ⁰ F)
Shade Available	Various
Shelf Life	One Year
Packing Available	20 Ltrs., 4 Ltrs., 1 Ltrs., 500 ml., 200 ml.,

APPLICATION PROCEDURE:

- The substrate must be free from oil and other contaminants.
- Sandblasting is required to Sa 2 ½, if sandblasting is not possible, manual wire brushing is recommended. Use Paint Remover to remove away rust and rinse with water and let it dry. Apply 1- 2 coats of red oxide primer by roller, brush or spray or 1 – 2 coats of undercoat before the application of HI – GLOSS ENAMEL.