



TARALAC®

TARA PAINTS & CHEMICALS

(An ISO 9001:2015 Certified Company)

A - 423 / 14, Mahagujarat Industrial Estate, Sarkhej - Bavla Road, Lane Behind Satyam Arcade,
Village : Moraiya, Ahmedabad - 382 210, Gujarat (India)

Tel: (F): +91 8000011774, E-mail: taralac@hotmail.com , taralac@taralac.com Website: www.taralac.com

1412 Syn Black Board Green

Syn Enamel Paint is a Single Pack First Quality Hi-Gloss Alkyd Enamel Paint, used multi-purposely on various substrates.

ADVANTAGES:

- For interior and exterior surfaces like masonry, steel, wood, asbestos etc.
- Weather resistance and exterior protection.
- Good colour retention.
- Ease of application.
- Excellent for wood and metal surfaces.
- Good hiding power and adhesion.
- Super glossy finish.

TECHNICAL DATA

Areas of application	Wood, Asbestos, masonry, Metal etc.
Thinner recommended	Taralac St Thinner ST – 2
Method of application	Brushing or Spraying
Drying time	Surface dry – 1 – 2 hr Hard dry - less than 18 hours
Viscosity	70 – 80 sec
Volume Solids	Approx 48 – 58%
Specific Graviry	0.90 – 1.15 kg/lt
Finish	Smooth and Glossy
Covering capacity (spreading by brushing on smooth non-absorbent surface)	18 - 24 sq. Mts./ltr/coat depending upon the nature of the substrate at 20 - 25 microns film thickness
Flash Point	Above 30 ⁰ C (86 ⁰ F)
Shade Available	Various
Shelf Life	One Year
Packing Available	20 Ltrs., 4 Ltrs., 1 Ltrs., 500 ml., 200 ml.,

APPLICATION PROCEDURE:

- The substrate must be free from oil and other contaminants.
- Sandblasting is required to Sa 2 ½, if sandblasting is not possible, manual wire brushing is recommended. Use Paint Remover to remove away rust and rinse with water and let it dry. Apply 1- 2 coats of red oxide primer by roller, brush or spray or 1 – 2 coats of undercoat before the application of HI – GLOSS ENAMEL.

All the information given here are as per the results obtained in laboratory & are given in good faith to guide the user but without any warranty, the actual application results might vary depending on the conditions. We are not responsible for any loss, injury or damage resulting from the use of this information