

1475 Hammertone Shades

Taralac Fast Drying Auto finish is prepared to form high-quality synthetic resin & exterior pigments & is formulated to dry quickly & high gloss. It does not need rubbing application of clear coat for gloss.

TECHNICAL DATA

Areas of application	Automotive, Machinery, Wood, Asbestos, masonry, Metal etc.
Thinner recommended	Taralac Stove Thinner ST – 1, 555, 111
Method of application	Spraying
Drying time	Surface dry - 10 minutes Tack Free - 1 Hour 30 minutes Recoating Time – 16-20 hours Full Cure - 48 hours
Finish	Smooth and Glossy
Specific Gravity	0.98 - 1.15 ± 3% (depending on shade)
Viscosity	110 ± 10 Sec by ford cup No.4 at 30C
Covering capacity	100 - 125 sq. ft./ltr/coat
(spreading by brushing on smooth non-absorbent surface)	upon the nature of the substrate at 25 - 23 microns film thickness
Flash Point	Above 30° C (86° F)
Gloss	Glossy - > 85%, Matt - <35%
Scratch Hardness	1200 gms
Shade Available	As per Shade Card
Flexibility	No Cracking or Peeling on 1/8" mandrel
Packing Available	20 Ltrs., 4 Ltrs., 1 Ltrs., 500 ml., 200 ml. depending on shades

Recommended Use:

Cost-effective high gloss enamel paint for Auto-finish & for industrial use.

Note: Taralac FD Auto finish can also be used in combination with PU hardness to achieve extra hardness