



TARALAC®

TARA PAINTS & CHEMICALS

(An ISO 9001:2015 Certified Company)

A - 423 / 14, Mahagujarat Industrial Estate, Sarkhej - Bavla Road, Lane Behind Satyam Arcade,
Village : Moraiya, Ahmedabad - 382 210, Gujarat (India)

Tel: (F): +91 8000011774, E-mail: taralac@hotmail.com , taralac@taralac.com Website: www.taralac.com

2204 Laccolite Black

Introduction:

A hard coating compared to Rubber Coat, Chassis Black & Anti-corrosive black
An anticorrosive & waterproofing paint, composed of bitumen, volatile organic solvent & special minerals, & specialized resins is considered having one of the best, cheapest & easy applicability. It is required for the following properties

- Anticorrosive properties.
- Acid & Alkali Resistance
- Termite resistance
- High adhesion to any kind of substrate.

TECHNICAL DATA

| | |
|---|---|
| Uses | Metal, Masonry & Wood etc. |
| Thinner | Taralac Syn. Thinner ST – 2 |
| Method of application | Brushing, Spraying or dipping |
| Sp.Gr. at 27° C | 0.90 to 1.0 |
| Covering capacity | 10 - 14 sq. Mts./lt/coat depending on the porosity of the surface and |
| (Spreading by brushing on smooth Non-absorbent surface) | Upon the nature of substrate at 20 - 25 microns film thickness on the non-adsorbent surface |
| Flash Point | Above 60° C |
| Shade Available | Black |
| Packing Available | 200lt, 20lt, 4lt, 1lt, 500 ml, 200 ml. |
| Ductility at 27° C | 2 or more than 2 |
| Areas of Application | <ul style="list-style-type: none">• As road marking paint• On TMT bars used for construction• For waterproofing, Damp Proofing, Mastic asphalt for roads & floors, Foam Concreting. On terrace floors or to fill cracks.• On any metal surface (pipes, bars, etc.)• On old painted surfaces.• Over brick masonry & Concrete.• Thick Coat As a Sound Proofing• Before wooden Paneling |

Direction for use:

Ensure that the surface to be painted is free from loose matter, dust etc.

Apply a coat of paint by brushing after adjustment consistency using the recommended thinner. It can also be applied by spray applications.

Note:

The container should be stored in tight lid, under the shed.
Should not be exposed to naked flames.