



**TARALAC®**

# TARA PAINTS & CHEMICALS

(An ISO 9001:2015 Certified Company)

A - 423 / 14, Mahagujarat Industrial Estate, Sarkhej - Bavla Road, Lane Behind Satyam Arcade,  
Village : Moraiya, Ahmedabad - 382 210, Gujarat (India)

Tel: (F): +91 8000011774, E-mail: taralac@hotmail.com , taralac@taralac.com Website: www.taralac.com

## 2206 Chlorinated Rubber Paint

A chlorinated, rubber-based coating designed to withstand continuous submersion and the effects of wear and weather.

### ADVANTAGES:

- (1). Weather Resistant
- (2). Highly Durable
- (3). Chemical Resistant
- (4). Water-Resistant
- (5). Self Priming

### TECHNICAL DATA

Areas of application	Swimming Pools, Fountains, Concrete, Plaster, Ponds, Reflection Basins
Thinner recommended	Taralac Stoving Thinner ST – 1
Method of application	Spraying or Brushing
Drying time	Surface dry - 10 minutes Recoating Time - 16-20 hours Full Cure - 48 hours
Finish	Smooth and Satin
The viscosity of Finish Paint at 30C by FC 4	55 – 65 sec
Covering capacity (spreading by brushing on the smooth non-absorbent surface)	20 - 24 sq. Mts./ltr/coat depending upon the nature of substrate at 20 - 25 microns film thickness.
Flash Point	Above 30 <sup>0</sup> C (86 <sup>0</sup> F)
Gloss	Semi-Gloss
Shade Available	As per Shade Card
Flexibility	No Cracking or Peeling on 1/8” mandrel
Packing Available	20 Ltrs., 4 Ltrs., 1 Ltrs.,

### SURFACE PREPARATION:

The surface must be clean, and free of all contamination before application. Etch surface for best results. Surface may be damp but not wet prior to etching. Consult your Griggs representative for specific surface preparation instructions. Allow 7 - 10 days of dry weather before filling pool. For each day of rain, allow 2 additional days of drying. Do not apply if rain threatens.

All the information given here are as per the results obtained in laboratory & are given in good faith to guide the user but without any warranty, the actual application results might vary depending on the conditions. We are not responsible for any loss, injury or damage resulting from the use of this information

PDS Ver.No. 2206.01/27122021