



TARALAC®

TARA PAINTS & CHEMICALS

(An ISO 9001:2015 Certified Company)

A - 423 / 14, Mahagujarat Industrial Estate, Sarkhej - Bavla Road, Lane Behind Satyam Arcade,
Village : Moraiya, Ahmedabad - 382 210, Gujarat (India)

Tel: (F): +91 8000011774, E-mail: taralac@hotmail.com , taralac@taralac.com Website: www.taralac.com

2509 HR Shades 200-250 C

Taralac HR Paint is based on silicon modified Resins. Brilliant lustre, excellent durability and corrosion resistance are the other main properties of Taralac HR Shades. It is supplied in a single pack system. Taralac HR PAINT is fast drying and has excellent adhesion, hardness and flexibility and also good water resistance.

Taralac HR PAINT is suitable for surfaces susceptible to atmosphere corrosion and in environments where good durability is required. Good heat-resisting properties and high covering capacity coupled with long life make this paint the most desired coating from the point of view of economy and performance.

The paint is widely used for steel structures such as Chimneys, Boilers, Ovens, Furnace Parts, Automobile Exhaust, Etc.

Grade	200 - 250° C
Viscosity of Supply	60 – 90 secs. By Ford Cup B-4 at 30°C
Thinner	Thinner – 555, 111 or 091
Application Viscosity	15-20 secs. By Ford Cup B-4 at 30°C
Specific Gravity	1.00 ± 3%
Method of Application	Brushing Spraying at a pressure of 2.75 to 3.5 kgs/ cm ² (40-50 p.s.i.)
Covering capacity (Spreading by brushing on smooth mild steel surface)	6 – 8 sq. meters. / Lt. per coat
Drying time [@28-30°C & 60 + 5% R.H.]	Surface Dry - not more than 2 hours. Hard Dry – not more than 18 hours.
Flashpoint (Abel's closed cup)	Above 30°C (86 °F)
Packs Available	1, 4, 20 Lt

Surface Preparation

The surface should be free from dirt, dust, grease, rust and moisture. Degreasing and de-rusting can be done by suitable treatment. Stir well before use. It is supplied at a consistency, suitable for brushing and spraying. HR Paint or aluminium Paint should be applied on bare metal & no primers should be used.

For the application of two or more coats, an interval of 8 hours should be allowed between any two coats.

(This information is given in good faith but without warranty. Covering capacity is indicated on the basis of results obtained on a prepared smooth surface).